



OmniPro™
CPP TF20

20% Talc Reinforced, Copolymer Polypropylene

PHYSICAL	Units	ASTM/ISO Procedure	English	Metric
Melt Flow	g/10 min.	D1238	10	10
Specific Gravity		D792	1.04	1.04
Filler/Reinforcement	%	D2584	20	20

IMPACT

Izod Impact Resistance Notched 1/8" bar, 73°F	ft.-lbs/in. (J/m)	D256	1.8	96
--	-------------------	------	-----	----

MECHANICAL

Tensile Strength At Yield, 73°F	psi (MPa)	D638	3,500	24
Tensile Elongation	%	D638	45	45
Flexural Modulus	psi (MPa)	D790	225,000	1,553
Flexural Strength	psi (MPa)	D790	8,500	59

THERMAL

Deflection Temperature 1/8" bar, 66 psi	°F (°C)	D648	210	99
1/8" bar, 264 psi	°F (°C)	D648	140	60

FLAMMABILITY

Flame Resistance *Omni Internal Testing	.125"	UL94	HB*	HB*
--	-------	------	-----	-----

RECOMMENDED PROCESSING CONDITIONS

Drying Temperature	N/A
Drying Time	N/A
Maximum Moisture	N/A
Rear Zone(s)	400 to 480° F
Middle Zone(s)	420 to 500° F
Front Zone(s)	420 to 500° F
Nozzle	420 to 500° F
Mold Temperature	80 to 140° F
Melt Temperature	420 to 500° F
Back Pressure	50 to 100 psi

Values are based on natural or black materials unless otherwise noted. Properties and values herein are based on laboratory test specimens and should not be used to establish minimum specification limits or fabricate tooling.

Omni does not guarantee the accuracy of this information or the suitability of this product in any given application or usage situation.