



**OmniPro™**  
**HPP CCF20**

20% CaCO<sub>3</sub> Reinforced, Homopolymer Polypropylene

PHYSICAL	Units	ASTM/ISO Procedure	English	Metric
Melt Flow	g/10 min.	D1238	10	10
Specific Gravity		D792	1.04	1.04
Filler/Reinforcement	%	D2584	20	20

**IMPACT**

Izod Impact Resistance Notched 1/8" bar, 73°F	ft.-lbs/in. (J/m)	D256	0.8	43
--	-------------------	------	-----	----

**MECHANICAL**

Tensile Strength At Yield, 73°F	psi (MPa)	D638	4,000	28
Tensile Elongation	%	D638	50	50
Flexural Modulus	psi (MPa)	D790	280,000	1,932
Flexural Strength	psi (MPa)	D790	7,500	52

**THERMAL**

Deflection Temperature 1/8" bar, 66 psi	°F (°C)	D648	235	113
1/8" bar, 264 psi	°F (°C)	D648	180	82

**FLAMMABILITY**

Flame Resistance *Omni Internal Testing	.125"	UL94	HB*	HB*
--	-------	------	-----	-----

**RECOMMENDED PROCESSING CONDITIONS**

Drying Temperature	N/A
Drying Time	N/A
Maximum Moisture	N/A
Rear Zone(s)	400 to 480° F
Middle Zone(s)	420 to 500° F
Front Zone(s)	420 to 500° F
Nozzle	420 to 500° F
Mold Temperature	80 to 140° F
Melt Temperature	420 to 500° F
Back Pressure	50 to 100 psi

Values are based on natural or black materials unless otherwise noted. Properties and values herein are based on laboratory test specimens and should not be used to establish minimum specification limits or fabricate tooling.

Omni does not guarantee the accuracy of this information or the suitability of this product in any given application or usage situation.