



OmniTech™
PBT GB30
 Glass Bead Reinforced PBT

PHYSICAL	Units	ASTM/ISO Procedure	English	Metric
Specific Gravity		D792	1.52	1.52
Filler/Reinforcement	%	D2584	30	30
IMPACT				
Izod Impact Resistance Notched 1/8" bar, 73 °F	ft.-lbs/in. (J/m)	D256	0.8	43
MECHANICAL				
Tensile Strength, Yld.	psi (MPa)	D638	7,200	50
Tensile Elongation	%	D638	3	3
Flexural Modulus	psi (MPa)	D790	600,000	4,137
Flexural Strength	psi (MPa)	D790	12,900	89
THERMAL				
Deflection Temperature 1/8" bar, 264 psi	°F (°C)	D648	280	130
FLAMMABILITY				
Flame Resistance *Omni Internal Testing		UL94	HB*	HB*
RECOMMENDED PROCESSING CONDITIONS				
Drying Temperature			220° F	
Drying Time			3-6 hrs. max.	
Maximum Moisture			0.02%	
Rear Zone(s)			480 to 520° F	
Middle Zone(s)			480 to 530° F	
Front Zone(s)			480 to 530° F	
Nozzle			480 to 530° F	
Mold Temperature			80 to 180° F	
Melt Temperature			480 to 520° F	
Back Pressure			50 to 100 psi	

Values are based on natural or black materials unless otherwise noted. Properties and values herein are based on laboratory test specimens and should not be used to establish minimum specification limits or fabricate tooling.

Omni does not guarantee the accuracy of this information or the suitability of this product in any given application or usage situation.