



OmniTech™
PMA IM UV

Impact Modified, UV Stabilized, PMMA

PHYSICAL	Units	ASTM/ISO Procedure	English	Metric
Melt Flow	g/10 min	D1238	8	8
Specific Gravity		D792	1.06	1.06
Mold Shrinkage, Isotropic	in/in	D955	.003 to .007	
IMPACT				
Izod Impact Resistance Notched 1/8" bar, 73°F	ft.-lbs/in. (J/m)	D256	1.2	64
MECHANICAL				
Tensile Strength At Yield, 73°F	psi (MPa)	D638	6,800	47
Tensile Elongation	%	D638	30	30
Flexural Modulus	psi (MPa)	D790	250,000	1,724
Flexural Strength	psi (MPa)	D790	8,500	59
THERMAL				
Deflection Temperature 1/8" bar, 66 psi	°F (°C)	D648	-	-
1/8" bar, 264 psi	°F (°C)	D648	205	96
FLAMMABILITY				
Flame Resistance *Omni Internal Testing	.125"	UL94	HB*	HB*
RECOMMENDED PROCESSING CONDITIONS				
Drying Temperature			190° F	
Drying Time			4 hrs. max.	
Maximum Moisture			0.02%	
Rear Zone(s)			400 to 480° F	
Middle Zone(s)			420 to 500° F	
Front Zone(s)			420 to 500° F	
Nozzle			420 to 500° F	
Mold Temperature			80 to 140° F	
Melt Temperature			420 to 500° F	
Back Pressure			50 to 100 psi	

Values are based on natural or black materials unless otherwise noted. Properties and values herein are based on laboratory test specimens and should not be used to establish minimum specification limits or fabricate tooling.

Omni does not guarantee the accuracy of this information or the suitability of this product in any given application or usage situation.