



OmniCarb™
PC 110

Medium Viscosity, Injection Molding Grade, Polycarbonate

PHYSICAL	Units	ASTM/ISO Procedure	English	Metric
Melt Flow	g/10 min.	D1238	10	10
Specific Gravity		D792	1.2	1.2
IMPACT				
Izod Impact Resistance Notched 1/8" bar, 73 °F	ft.-lbs/in. (J/m)	D256	14	743
MECHANICAL				
Tensile Strength At Yield, 73 °F	psi (MPa)	D638	8,800	61
Tensile Elongation	%	D638	7	7
Flexural Modulus	psi (MPa)	D790	330,000	2,277
Flexural Strength	psi (MPa)	D790	13,000	90
THERMAL				
Deflection Temperature 1/8" bar, 66 psi	°F (°C)	D648	280	138
1/8"bar, 264 psi	°F (°C)	D648	260	127
FLAMMABILITY				
UL File Number E138590				
Flame Resistance	.059" (1.5 mm)	UL94	HB	HB
Flame Resistance	.118" (3.0 mm)	UL94	HB	HB
Relative Thermal Index		UL746B	176 °F/176 °F/176 °F	80 °C/80 °C/80 °C
All Color Recognition				
RECOMMENDED PROCESSING CONDITIONS				
Drying Temperature			250 °F	
Drying Time			3 to 4 Hours	
Maximum Moisture			0.02%	
Rear Zone(s)			480 to 560 °F	
Middle Zone(s)			520 to 580 °F	
Front Zone(s)			520 to 580 °F	
Nozzle			520 to 580 °F	
Mold Temperature			120 to 220 °F	
Melt Temperature			520 to 580 °F	
Back Pressure			25 to 50 psi	

Omni does not guarantee the accuracy of this information or the suitability of this product in any given application or usage situation. Values are based on natural materials unless otherwise noted. The addition of pigments and colorants can significantly affect final Properties. The Data and values herein are based on laboratory test specimens and should not be used to establish specification limits or fabricate tooling.