



OmniLon™
PA612 GR40

40% Glass Reinforced, Nylon 6/12

PHYSICAL	Units	ASTM/ISO Procedure	English	Metric
Specific Gravity		D792	1.36	1.36
Filler/Reinforcement	%	D5630	40	40
IMPACT				
Izod Impact Resistance Notched 1/8" bar, 73°F	ft.-lbs/in. (J/m)	D256	2.6	139
MECHANICAL				
Tensile Strength At Yield, 73°F	psi (MPa)	D638	25,500	176
Tensile Elongation	%	D638	3	3
Flexural Modulus	psi (MPa)	D790	1,400,000	9,653
Flexural Strength	psi (MPa)	D790	38,500	265
THERMAL				
Deflection Temperature 1/8" bar, 66 psi	°F (°C)	D648	425	218
1/8" bar, 264 psi	°F (°C)	D648	420	216
FLAMMABILITY				
Flame Resistance *Omni Internal Testing	.125"	UL94	HB*	HB*
RECOMMENDED PROCESSING CONDITIONS				
Drying Temperature			175° F	
Drying Time			2 to 4 Hours	
Maximum Moisture			0.20%	
Rear Zone(s)			480 to 540° F	
Middle Zone(s)			500 to 560° F	
Front Zone(s)			500 to 560° F	
Nozzle			520 to 560° F	
Mold Temperature			80 to 180° F	
Melt Temperature			510 to 560° F	
Back Pressure			50 psi	

Values are based on natural or black materials unless otherwise noted. Properties and values herein are based on laboratory test specimens and should not be used to establish minimum specification limits or fabricate tooling.

Omni does not guarantee the accuracy of this information or the suitability of this product in any given application or usage situation.