



OmniLon™ PAA GR30 HS

30% Glass Reinforced, Reduced Moisture Absorption, Heat Stabilized, Polyamide Performance Compound

PHYSICAL	Units	ASTM/ISO Procedure	English	Metric
Specific Gravity		D792	1.37	1.37
Filler/Reinforcement	%	D5630	30	30
IMPACT				
Izod Impact Resistance Notched 1/8" bar, 73°F	ft.-lbs/in. (J/m)	D256	2.4	128
MECHANICAL				
Tensile Strength At Yield, 73°F	psi (MPa)	D638	24,000	166
Tensile Elongation	%	D638	4	4
Flexural Modulus	psi (MPa)	D790	1,200,000	8,274
Flexural Strength	psi (MPa)	D790	38,000	262
THERMAL				
Deflection Temperature 1/8" bar, 66 psi	°F (°C)	D648	500	260
1/8" bar, 264 psi	°F (°C)	D648	475	246
FLAMMABILITY				
Flame Resistance *Omni Internal Testing	.125"	UL94	HB*	HB*
RECOMMENDED PROCESSING CONDITIONS				
Drying Temperature			250° F	
Drying Time			4 Hours	
Maximum Moisture			0.20%	
Rear Zone(s)			605 to 615° F	
Middle Zone(s)			615 to 625° F	
Front Zone(s)			620 to 630° F	
Nozzle			620 to 630° F	
Mold Temperature			150 to 200° F	
Melt Temperature			625 to 650° F	
Back Pressure			50 to 100 psi	

Values are based on natural or black materials unless otherwise noted. Properties and values herein are based on laboratory test specimens and should not be used to establish minimum specification limits or fabricate tooling.

Omni does not guarantee the accuracy of this information or the suitability of this product in any given application or usage situation.